

# FLOORFINDER COMPACT plus FF

Heavy duty industrial flooring system based on high strength coloured epoxy screed for protection of concrete floor surface withstanding harsh and aggressive service conditions such as very heavy mechanical abuses and chemical attacks.

### Application Fields

**Engineering industry** 

Food and beverage industry

Pharmaceutical industry

Paper industry

Military areas with high mechanical load

**High-bay warehouses** 

#### FLOORFINDER EP-T707/P FF

or EP-T708/P FF
SYNTHETIC
RESIN
SCREED

#### FLOORFINDER EP-T703<sup>FF</sup>

PRIMER



## SYSTEM BUILD UP



FLOORFINDER
UREA S6400 FF

PORE
SEALER

## **SYSTEM HIGHLIGHTS**

5.0 - 9.0 mm System thickness



High abrasion resistance



Liquid tight surfaces possible



Low emission acc. AgBB and other standards



Suitable for forklift, trucks and tracked vehicles



chemical resistance



Diverse colours available



Light to medium anti-skid surface



Extremely high mechanical load and impact resistance









## FLOORFINDER COMPACT FF

## **Application and Consumption**

Layer	Product	Consumption (kg/m²)	Sand broadcasting (kg/m²)	Thickness (mm)	Application
(Optional) Seal coat, matt transparent	FLOORFINDER PU-S6005 FF	0.10 - 0.12	-	0.08 - 0.10	microfiber roller
(Optional)  Pore sealer 1 – 3 layers  w/ thixotropic agent	FLOORFINDER UREA S6400 FF + 0.5 % FLOORFINDER X955 FF	ca. 0.4 – 0.5 0.05 – 0.15		0.2 - 0.25 0.1 - 0.15	hard rubber squeegee, trowel
Synthetic resin screed (epoxy screed)	FLOORFINDER EP-T707/P FF Or FLOORFINDER EP-T708/P FF	ca. 2.0 kg/mm mortar	-	4.5 – 9.0	Trowel, smoothing trowel (power plate)
Primer	FLOORFINDER EP-T703 FF or other	ca. 0.4	ca. 0.5	ca. 0.5	roller or rubber squeegee
Substrate	Cementitious substrates according to the appropriate standards and approvals must be capable of bearing loads and be free of cracks and voids. Pull-off strength ≥ 1.5 N/mm², residual moisture content < 4 %-CM, with higher residual moisture and on substrates with moisture from the backside special measures must be taken or a damp proof membrane must be installed. Substrate preparation e.g. grinding or shot blasting, sweeping and vacuum-cleaning is mandatory. Consumptions are calculated with FLOORFINDER quartz sands and fillers. Usage of other quartz sands and fillers can cause changes of consumption and technical data.				
Note	Detailed application instructions are available upon request or refer to the technical product data sheet.				

#### **Technical Data**



property	standard	result
Flexural strength mortar	EN 196 / ASTM C190	Ca 18 - 24 N/mm²
Compressive strength	EN 196 / ASTM C190	Ca 65 - 89 N/mm²
Adhesive strength	EN ISO 4624	> 1.5 N/mm²
Shore-Hardness	DIN ISO 868	D 80 after 28 d
Water absorption coefficient	EN 1062-3	< 0,01 kg/(m² x h0,5)
Heat resistance hot water		max. 80°C short time spillages max. 60°C Permanent
Impact strength	DIN EN 13813	≥ 4 Nm (IR4)
Wear resistance (Böhme)	DIN 51963	ca. 6.1 cm <sup>3</sup> / 50 cm <sup>2</sup>
Chemical resistant	DiBT test liquids	Nr 1,3,10,11
Anti-skid properties	BGR 181 / DIN 51130	Class R10

Remark: for further information please refer to the product data sheets or contact our technical service. All data are approximate values. Therefore, no liability claims can be derived from the system data sheet. As all FLOORFINDER data sheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue (see www.floorfinder.com.my or contact us directly)– all technical information is subject to change without prior notice. FLOORFINDER products are guaranteed against defective material and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies which can be obtained on request.