

FLOORFINDER DECK 11b plus^{FF}

Car park deck coating system with combined membrane and wear coat with enhanced crack bridging properties (class B 3.2) for multi storey car parks in intermediate decks with pedestrian and vehicle traffic. In accordance with DIN EN 1504-2 and DIN V 18026, class OS 11b/OS Fb.

Application Fields

Intermediate decks

Covered top decks

Sidewalks on bridges



SYSTEM BUILD UP





SYSTEM HIGHLIGHTS

1.5 - 5.5 mm System thickness



PRIMER

High abrasion resistance



Very high colour and UV stability with PU sealer



Fire resistance class B_{fl-s}1



Crack bridging class B3.2



Good chemical resistance against gasoline and others



Many colours available



Slip resistant surface for car traffic and pedestrian



Class OS 11b, OS Fb EN 1504-2 DIN V 18026









FLOORFINDER DECK 11b plus FF

Application and Consumption

Layer	Product	Consumption (kg/m²)	Sand broadcasting (kg/m²)	Thickness (mm)	Application	
Sealer, UV-resistant	FLOORFINDER PU-S650FF	0.10 – 0.12 (minimum 2 coats)	none	ca. 0.05 – 0.10	rubber squeegee, roller for finish	
(Alternatively) Seal coat	FLOORFINDER EP-S602 ^{FF} or FLOORFINDER EP-S600 ^{FF}	0.6 - 0.9	none	0.5 – 0.7	rubber squeegee, roller for finish	
Wear coat (HWO1)	FLOORFINDER PU-L310FFFF	0.6 – 1.2	QS 0.3-0.8 or 0.6-1.2 mm in excess	min. 2.5	notched trowel	
(optional) Levelling layer/scratch coat	FLOORFINDER EP-T703 ^{FF} + QS 0.1 – 0.4 mm	0.5 - 1.5 + QS 25-150 %	QS 0.3-0.8 mm In excess	0.5 – 1.5	notched trowel, roller for finish	
Primer	FLOORFINDER EP-T703 ^{FF}	0.3 – 0.5	QS 0.3-0.8 mm 0.5 – 0.8	ca. 0.3	roller or rubber squeegee	
Substrate	Cementitious substrates according to the appropriate standards and approvals must be capable of bearing loads and be free of cracks and voids. Pull-off strength ≥ 1.5 N/mm², residual moisture content < 4 %-CM, with higher residual moisture and on substrates with moisture from the backside special measures must be taken or a damp proof membrane must be installed. Substrate preparation e.g. grinding or shot blasting, sweeping and vacuum-cleaning is mandatory. Consumptions are calculated with FLOORFINDER quartz sands and fillers. Usage of other quartz sands and fillers can cause changes of consumption and technical data.					
Note	Detailed application instructions are available upon request or refer to the technical product data sheet					

Technical Data

	Property	Standard	Result			
	Adhesive strength at T _{NORM}	DIN EN 1542	≥ 2.3 N/mm² (≥ 1.5 N/mm²)			
	Adhesive strength after freeze-thaw with de-icing salt	DIN EN 13687-1 and -2	≥ 1.7 N/mm² (≥ 1.5 N/mm²)			
	Dynamic crack bridging (-20°C)	DIN EN 1062-7	II _{T+V} (B3.2)			
	Grip and slip resistant	DIN EN 13036-4 DIN 51130	60 Skt (≥ 55 Skt) R11-V4 and R12-V6			
	Chemical resistance	DIN EN 13529	Test liquids DiBT Nr 1, 3, 10			
	Abrasion resistance (H22 wheel)	DIN EN ISO 5470-1	1.270 mg /1000 U (≤ 3.000)			
	Carbon dioxide permeability	DIN EN 1062-6	Class III > 1.200 m (> 50 m)			
	Water vapour permeability	DIN EN ISO 7783-1 and -2	Class III > 200 m (> 50 m)			
	Water absorption coefficient	DIN EN 1062-3	< 0.01 kg/m ² x h ^{0,5} (< 0.1)			
	Impact resistance	DIN EN ISO 6772-2	4 Nm – no cracks			
	Fire behaviour class system	EN 13501-1	B _{ff} -s1			
	,		"			

Remark: for further information please refer to the product data sheets or contact our technical service. All data are approximate values. Therefore, no liability claims can be derived from the system data sheet. As all FLOORFINDER data sheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue (see www.floorfinder.com.my or contact us directly)- all technical information is subject to change without prior notice. FLOORFINDER products are guaranteed against defective material and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies which can be obtained on request.