

FLOORFINDER

DECK OS8 FF

Parking deck coating system for ramps, spirals and underground garages with pedestrian and vehicle traffic and for slip resistant industrial floors with medium to heavy load. According to DIN EN 1504-2 and DIN V 18026, class OS 8.

Application Fields

Ramps and spirals

Underground garages

Slip resistant industrial floors

SYSTEM BUILD UP


FLOORFINDER
EP-S600^{FF}
SEALER



FLOORFINDER
EP-T703^{FF}
PRIMER



LINE MARKING
E.G PU or EPOXY



SYSTEM HIGHLIGHTS

1.5 – 2.5 mm System thickness



High wear and abrasion resistance



Liquid tight surfaces



Economic system build-up



Fire resistance class B_{fl-s}1



Good chemical resistance against gasoline and others



Many colours available



Slip resistant surface for car and pedestrian traffic



OS 8
EN 1504-2
DIN V 18026



FLOORFINDER **DECK OS8^{FF}**

Application and Consumption

Layer	Product	Consumption (kg/m ²)	Sand broadcasting (kg/m ²)	Thickness (mm)	Application
(Alternative, not tested acc. OS 8) Sealer, UV-resistant	FLOORFINDER PU-S650 ^{FF}	0.6 – 0.9	none	0.5 – 0.7	rubber squeegee, roller for finish
Seal coat	FLOORFINDER EP-S600 ^{FF} or FLOORFINDER EP-S602 ^{FF}	0.55 – 0.9	none	0.5 – 0.7	rubber squeegee, roller for finish
Scratch primer	FLOORFINDER EP-T703 ^{FF} + QS 0.1 – 0.4 mm	0.45 – 0.8 + QS 50 %	QS 0.3-0.8 mm In excess	1.5 – 2.5	notched trowel, roller for finish
(optional) Blocking primer ≤ 6 % CM	FLOORFINDER EP-P210 ^{FF} oder EP-T703 ^{FF}	0.4 – 0.6	none	ca. 0.3	roller or rubber squeegee
Substrate	Cementitious substrates according to the appropriate standards and approvals must be capable of bearing loads and be free of cracks and voids. Pull-off strength ≥ 1.5 N/mm ² , residual moisture content < 4 %-CM, with higher residual moisture and on substrates with moisture from the backside special measures must be taken or a damp proof membrane must be installed. Substrate preparation e.g. grinding or shot blasting, sweeping and vacuum-cleaning is mandatory. Consumptions are calculated with FLOORFINDER quartz sands and fillers. Usage of other quartz sands and fillers can cause changes of consumption and technical data.				
Note	Detailed application instructions are available upon request or refer to the technical product data sheet.				

Technical Data

Property	Standard	Result
Adhesive strength at TNORM	DIN EN 1542	≥ 4.3 N/mm ² (≥ 2.0 N/mm ²)
Adhesive strength after freeze-thaw with de-icing salt	DIN EN 13687-1 and -2	≥ 4.3 N/mm ² (≥ 2.0 N/mm ²)
Dynamic crack bridging (-20°C)	DIN EN 1062-7	NPD
Grip and slip resistant	DIN EN 13036-4 DIN 51130	60 Skt (≥ 55 Skt) R11-V4 and R12-V6
Chemical resistance	DIN EN 13529	Test liquids DiBT Nr. 1, 3, 10
Abrasion resistance (H22 wheel)	DIN EN ISO 5470-1	1.903 mg /1000 U (≤ 3.000)
Carbon dioxide permeability	DIN EN 1062-6	Class III > 2.500 m (> 50 m)
Water vapour permeability	DIN EN ISO 7783-1 and -2	Class III > 200 m (> 50 m)
Water absorption coefficient	DIN EN 1062-3	< 0.01 kg/m ² x h ^{0.5} (< 0.1)
Impact resistance	DIN EN ISO 6772-2	4 Nm – no cracks
Fire behaviour class system	EN 13501-1	Bfl-s1

Remark: for further information please refer to the product data sheets or contact our technical service. All data are approximate values. Therefore, no liability claims can be derived from the system data sheet. As all FLOORFINDER data sheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue (see www.floorfinder.com.my or contact us directly)– all technical information is subject to change without prior notice. FLOORFINDER products are guaranteed against defective material and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies which can be obtained on request.

Manufacturer:

FLOORFINDER ASIA SDN. BHD. – A division of VIACOR VISION AG, SWITZERLAND | No. 28, Lorong Sungai Puloh 1A/KU6 | Jalan Sungai Puloh | Batu 5 3/4 Kapar | 42100 Klang | Selangor Darul Ehsan | Malaysia | Tel: +603 3290 7644 | info@floorfinder.com.my | www.floorfinder.com.my