### SYSTEM DATA SHEET

# floorfinder.

## FLOORFINDER **DECK rapid M** FF

Fast curing car park deck coating system with separate, manually applied waterproofing membrane and wear coat with enhanced crack bridging properties class B 4.2 (-20°C). For multi storey car parks with exposed and intermediate decks as well as sidewalks on bridges with pedestrian and vehicle traffic. According to 1) DIN EN 1504-2 and DIN V 18026; 2) RILI SIB 2001 class OS10; 3) DIN 183532 part 1 & 6

#### Application Fields

Exposed car park decks and covered intermediate decks

Roof decks with car traffic

Sidewalks on bridges





## floorfinder.

### FLOORFINDER **DECK rapid M<sup>FF</sup>**

### **Application and Consumption**

Layer	Product	Consumptio n (kg/m²)	Sand broadcasting (kg/m²)	Thickness (mm)	Application
Wear coat, fast curing	FLOORFINDER UREA S6001 P <sup>FF</sup>	2.5 - 3.0	none	1.5 -2.0	trowel, long- handled squeegee, roller
Highly elastic water proofing manually applied membrane	FLOORFINDER PU-L2000 <sup>FF</sup>	3.0 - 3.2	none	ca. 2.0	notched trowel
Primer	FLOORFINDER EP-T703FF	03 05	QS 0.3 – 0.8	ca. 0.3	roller or rubber squeegee
(Alternative) fast curing	FLOORFINDER EP-P210 SFF	0.5 - 0.5			
Substrate	Cementitious substrates according to the appropriate standards and approvals must be capable of bearing loads and be free of cracks and voids. Pull-off strength $\geq$ 1.5 N/mm <sup>2</sup> , residual moisture content < 4 %-CM, with higher residual moisture and on substrates with moisture from the backside special measures must be taken or a damp proof membrane must be installed. Substrate preparation e.g. grinding or shot blasting, sweeping and vacuum-cleaning is mandatory. Consumptions are calculated with FLOORFINDER quartz sands and fillers. Usage of other quartz sands and fillers can cause changes of consumption and technical data.				
Note	Detailed application instructions are available upon request or refer to the technical product data sheet.				

### **Technical Data**







Property	Standard	Result	
Adhesive strength at TNORM	DIN EN 1542	≥ 2.7 N/mm²	
Adhesive strength after freeze-thaw with de-icing salt	DIN EN 13687-1 and -2	1.6 N/mm²	
Dynamic crack bridging (-20°C)	DIN EN 1062-7	B4.2, IV <sub>T+V</sub>	
Grin and slin resistant	DIN EN 13036-4	≥ 55 Skt	
	DIN 51130	R11, V10	
Chemical resistance	DIN EN 13529	Test liquids DiBT Nr. 1, 3, 10	
Abrasion resistance (H22 wheel)	DIN ISO 9352, ASTM D 1044	< 700 mg / 1000 U	
Parking Abrasion Test (PAT)		VK 1 – Very low wear after 15.000 cycles	
Doppelhubtest	DIN EN 660-1:06	Loss of mass 0,0 g	
Carbon dioxide permeability	DIN EN 1062-6	Class III > 2.500 m	
Water vapour permeability	DIN EN ISO 7783-1 and -2	Class III > 200 m	
Water absorption coefficient	DIN EN 1062-3	< 0.01 kg/m² x h <sup>0,5</sup>	
Impact resistance	DIN EN ISO 6772-2	4 Nm – no cracks	
Fire classification	DIN EN 13501-1	B <sub>fl</sub> -s1	

Remark: for further information please refer to the product data sheets or contact our technical service. All data are approximate values. Therefore, no liability claims can be derived from the system data sheet. As all FLOORFINDER data sheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue (see www.floorfinder.com.my or contact us directly)– all technical information is subject to change without prior notice. FLOORFINDER products are guaranteed against defective material and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies which can be obtained on request.

#### Manufacturer:

FLOORFINDER ASIA SDN. BHD. - A division of VIACOR VISION AG, SWITZERLAND | No. 28, Lorong Sungai Puloh 1A/KU6 | Jalan Sungai Puloh | Batu 5 3/4 Kapar | 42100 Klang | Selangor Darul Ehsan | Malaysia | Tel: +603 3290 7644 | <u>info@floorfinder.com.my</u> | <u>www.floorfinder.com.my</u> Seite 2/2 Version Nr. 1 Stand: 08-2024