# floorfinder.


### SYSTEM DATA SHEET

## FLOORFINDER *ELASTIC SKY* FF

Decorative and elastic polyurethane coating system, very good UV- and colour stable, impact noise reducing, gentle to knees and joints, warm to feet, with good mechanical and chemical properties and a wide colour spectrum.







### **SYSTEM HIGHLIGHTS**

2.0 – 5.0 mm System thickness



## floorfinder.

### FLOORFINDER ELASTIC SKY FF

#### **Application and Consumption**

Layer	Product	Consumptio n (kg/m²)	Sand broadcasting (kg/m²)	Thickness (mm)	Application	
Sealer flexible, transparent, matt	FLOORFINDER PU- S6000 <sup>FF</sup>	0.12 - 0.14	none	0.11 - 0.13	roller or rubber squeegee and roller	
Decorative, self-levelling coating, UV and colour stable	FLOORFINDER PU- C500 SKY <sup>FF</sup> 20	2.0 - 2.5	none	2.0 -2.2	notched trowel	
(Recommended) Pore sealer	FLOORFINDER PU- C525 <sup>FF</sup>	0.6 – 1.0	none	ca. 0.5	notched trowel	
Primer	FLOORFINDER EP- T703 <sup>FF</sup> or others	ca. 04	QS 0.3 – 0.8 mm ca. 0.5	ca. 0.3	roller or rubber squeegee	
Substrate	Cementitious substrates according to the appropriate standards and approvals must be capable of bearing loads and be free of cracks and voids. Pull-off strength $\geq$ 1.5 N/mm <sup>2</sup> , residual moisture content < 4 %-CM, with higher residual moisture and on substrates with moisture from the backside special measures must be taken or a damp proof membrane must be installed. Substrate preparation e.g. grinding or shot blasting, sweeping and vacuum-cleaning is mandatory. Consumptions are calculated with FLOORFINDER quartz sands and fillers. Usage of other quartz sands and fillers can cause changes of consumption and technical data.					
Note	Detailed application instructions are available upon request or refer to the technical product data sheet.					

#### **Technical Data**

	Property	Standard	Result
	Tensile strength( top coating)	DIN 53504	ca. 9 N/mm²
	Elongation at break (top coating)	DIN 53504	ca. 60 %
	Tear resistance	DIN 53515	ca. 12 N/mm²
	Shore-Hardness	DIN ISO 868	80 A nach 28 d
	Way to use	In relating to DIN EN 685	Private buildings: 23 Public buildings: 34
	Impact sound reduction	DIN 4109	ca. 2 – 3 dB
	Impact strength	DIN EN 13813	≥ 4 Nm (IR4)
	Wear resistance (Taber)	ISO 9352, ASTM D 1044	≤ 80 mg
	Anti-skid surface	BGR 181 / DIN 51130	Class R9
	Adhesive strength	DIN ISO 4624	>1,5 N/mm²
	Fire behaviour class system	EN 13501-1	Bfl-s1

Remark: for further information please refer to the product data sheets or contact our technical service. All data are approximate values. Therefore, no liability claims can be derived from the system data sheet. As all FLOORFINDER data sheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue (see www.floorfinder.com.my or contact us directly)– all technical information is subject to change without prior notice. FLOORFINDER products are guaranteed against defective material and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies which can be obtained on request.

Manufacturer:

FLOORFINDER ASIA SDN. BHD. - A division of VIACOR VISION AG, SWITZERLAND | No. 28, Lorong Sungai Puloh 1A/KU6 | Jalan Sungai Puloh | Batu 5 3/4 Kapar | 42100 Klang | Selangor Darul Ehsan | Malaysia | Tel: +603 3290 7644 | <u>info@floorfinder.com.my</u> | <u>www.floorfinder.com.my</u> Seite 2/2 Version Nr. 1 Stand: 08-2024