floorfinder.

FLOORFINDER *ELASTIC comfort* FF

High elastic polyurethane coating system, with impact sound reducing rubber or foam mat, gentle to joints, temperature pleasing to the feet, with good mechanical and chemical properties and a wide colour spectrum.

Application Fields







SYSTEM DATA SHEET

floorfinder.

FLOORFINDER **ELASTIC comfort FF**

Application and Consumption

Layer	Product	Consumptio n (kg/m²)	Sand broadcasting (kg/m²)	Thickness (mm)	Application
Sealer, flexible, pigmented	FLOORFINDER PU-S6000 P ^{FF}	0.12 - 0.14	none	0.09 - 0.10	roller or rubber squeegee and roller
Self-levelling coating, high elastic	FLOORFINDER PU-C525 ^{FF}	2.0 - 3.0	none	1.5 – 2.2	notched trowel
(Recommended) Levelling layer	FLOORFINDER PU-C525 ^{FF}	0.6 - 1.0	none	ca. 0.5	notched trowel
Pore sealer	FLOORFINDER PU-L375FF	ca. 1.0	none	0.1 – 0.2	rubber squeegee or trowel
Elastic mat, adhesive	Elastic mat FLOORFINDER PU-B976 ^{FF}	4.0 – 6.0 mm ca. 0,8	none	4.0 - 6.0	roll out on fresh adhesive notched trowel
(Optional) Levelling layer	FLOORFINDER PU-C525 ^{FF}	0.6 - 1.0	none	ca. 0.5	notched trowel
Primer	FLOORFINDER EP-T703 ^{FF} or others	ca. 0.4	QS 0,3 – 0,8 mm ca. 0,5	ca. 0.3	roller or rubber squeegee
Substrate	rateCementitious substrates according to the appropriate standards and approvals must be capable of bearing loads and be free of cracks and voids. Pull-off strength ≥ 1.5 N/mm², residual moisture content < 4 %-CM, with higher residual moisture and on substrates with moisture from the backside special measures must be taken or a damp proof membrane must be installed. Substrate preparation e.g. grinding or shot blasting, sweeping and vacuum-cleaning is mandatory. Consumptions are calculated with FLOORFINDER quartz sands and fillers. Usage of other quartz sands and fillers can cause changes of consumption and technical data.Detailed application instructions are available upon request or refer to the technical product data sheet.				ure content < 4 %-CM, pecial measures must be iding or shot blasting, DORFINDER quartz sands
Note					product data sheet.

Technical Data



	Property	Standard	Result
-	Tensile strength (coating)	DIN 53504	ca. 9 N/mm²
-	Elongation at break (coating)	DIN 53504	ca. 200 %
-	Tear resistance	DIN 53515	ca. 15 N/mm²
- AL	Shore-Hardness	DIN ISO 868	80 A nach 28 d
-	Way of use	In relation to DIN EN 685	Private buildings: 23 Public buildings: 34
	Noice reduction	DIN 4109	ca. 12 – 20 dB
	Impact strength	DIN EN 13813	≥ 4 Nm (IR4)
	Wear resistance (Taber)	ISO 9352, ASTM D 1044	≤ 80 mg
	Anti skid properties	BGR 181 / DIN 51130	Class R9
	Adhesive strength	DIN ISO 4624	>1,5 N/mm²
	Fire behaviour system	EN 13501-1	Bfl-s1

Remark: for further information please refer to the product data sheets or contact our technical service. All data are approximate values. Therefore, no liability claims can be derived from the system data sheet. As all FLOORFINDER data sheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue (see www.floorfinder.com.my or contact us directly)- all technical information is subject to change without prior notice. FLOORFINDER products are guaranteed against defective material and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies which can be obtained on request.

Manufacturer:

 FLOORFINDER ASIA SDN. BHD. - A division of VIACOR VISION AG, SWITZERLAND | No. 28, Lorong Sungai Puloh 1A/KU6 | Jalan Sungai Puloh | Batu 5 3/4 Kapar | 42100 Klang |

 Selangor Darul Ehsan | Malaysia | Tel: +603 3290 7644 | info@floorfinder.com.my | www.floorfinder.com.my

 Version Nr. 1