

FLOORFINDER

PERM DECKFF

Slip resistant, water-vapour permeable epoxy advanced resin based coating system, low odour, low emission, hard-wearing, water-proof surface with good mechanical and chemical properties and a wide colour spectrum. According to DIN EN 1504-2 and DIN V 18026, class OS8.

Application Fields

Workshops

Production areas

Areas with moisture sensitive substrates

Private apartments

Paper mills

Metal working <u>industry</u>

Underground garages

Public buildings

FLOORFINDER EP-L380^{FF} WEAR

COAT



FLOORFINDER EP-P285^{FF}

PRIMER



SYSTEM BUILD UP



LINE MARKING

E.G PU or EPOXY



FLOORFINDER

EP-S680FF

SEALER



SYSTEM HIGHLIGHTS

1.5 - 3.0 mm System thickness



High water vapour permeable, no blistering due to hydrostatic pressure.



Seamless, liquid tight surfaces



Low emission acc. AgBB and other standards



OS 8 EN 1504-2 DIN V 18026



Good chemical resistance against gasoline and others



Extremely high mechanical load and impact resistance



Slip resistant surface for car and pedestrian traffic



Low odor









FLOORFINDER PERM DECK FF

Application and Consumption

Layer	Product	Consumption (kg/m²)	Sand broadcasting (kg/m²)	Thickness (mm)	Application	
Sealer, coloured, semi gloss	FLOORFINDER EP-S680 ^{FF}	0.6 – 0.9 + 3 - 5 % Water	none	0.5 – 0.8	roller or rubber squeegee + roller	
Wear coat with broadcasting with QS	FLOORFINDER EP-L380 ^{FF}	0.8 – 3.0	QS 0.3 – 0.8 In excess	0.5 – 1.6	trowel	
Primer	FLOORFINDER EP-P285 ^{FF}	0.3 – 0.4 + 15% Water	optional QS 0.3 – 0.8 0.3 – 0.5	0.15 - 0.3	roller	
Substrate	Cementitious substrates according to the appropriate standards and approvals must be capable of bearing loads and be free of cracks and voids. Pull-off strength ≥ 1.5 N/mm², this system is water vapour permeable, max. residual moisture < 6 - 8% CM, for magnesite screed <10% CM, anhydrite max. 1% residual moisture, attention for underfloorheating <0.3% CM, with higher residual moisture and on substrates with moisture from the backside special measures must be taken or a damp proof membrane should be installed. Substrate preparation e.g. grinding or shot blasting, sweeping and vacuum-cleaning is mandatory. Consumptions are calculated with FLOORFINDER quartz sands and fillers. Usage of other quartz sands and fillers can cause changes of consumption and technical data.					
Note	Detailed application instructions are available upon request or refer to the technical product data sheet.					

Technical Data

ANSWERS AND			
	Property	Standard	Result
1	Adhesive strength at T _{NORM}	DIN EN 1542	≥ 4,3 N/mm² (≥ 2,0 N/mm²)
31 Family	Adhesive strength after freeze-thaw with deicing salt	DIN EN 13687-1 and -2	≥ 4,3 N/mm² (≥ 2,0 N/mm²)
	Dynamic crack bridging (-20°C)	DIN EN 1062-7	NPD
	Grip and slip resistant	DIN EN 13036-4 DIN 51130	60 Skt (≥ 55 Skt) R11-V4 and R12-V6
	Chemical resistance	DIN EN 13529	Test liquids DiBT Nr. 1, 3, 10
	Abrasion resistance (H22 wheel)	DIN EN ISO 5470-1	1.903 mg /1000 U (≤ 3.000)
	Carbon dioxide permeability	DIN EN 1062-6	Class III > 2.500 m (> 50 m)
	Water vapour permeability	DIN EN ISO 7783-1 and -2	Class I > 4 m (< 5 m)
	Water absorption coefficient	DIEN EN 1062-3	< 0,01 kg/m ² x h0,5 (< 0,1)
	Impact resistance	DIN EN ISO 6772-2	4 Nm – no cracks
	Low emission	AgBB and M1	Fulfilled after 3 days
	Fire Resistance	EN 13501-1	Bfl-S1

Remark: for further information please refer to the product data sheets or contact our technical service. All data are approximate values. Therefore, no liability claims can be derived from the system data sheet. As all FLOORFINDER data sheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue (see www.floorfinder.com.my or contact us directly)- all technical information is subject to change without prior notice. FLOORFINDER products are guaranteed against defective material and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies which can be obtained on request.