
floorfinder.

SYSTEM DATA SHEET

FLOORFINDER **PERM conductive** FF

Conductive, water-vapour permeable epoxy advanced resin based coating system, low odour, low emission, hard-wearing, water tight surface with good mechanical and chemical properties and a wide colour spectrum. Conductive according to EN 1081 and EN 61340-5-1





Application Fields

floorfinder.

FLOORFINDER **PERM conductive FF**

Application and Consumption

Layer	Product	Consumption (kg/m²)	Sand broadcasting (kg/m²)	Thickness (mm)	Application	
Optional: Dissipative Floor Emulsion	TASKI Jontec ESD					
Self-levelling coating	FLOORFINDER EP-C5480 AS ^{FF}	2.8 - 4.0	none	2.0 - 3.0	notched trowel + spike roller	
Conductive layer incl. copper tape	FLOORFINDER EP-E480 ^{FF}	0.1 – 0.11 + 8 - 10 % Water	none	0.06 - 0.08	roller, squeegee + roller	
Scratch coat, levelling layer recommended	FLOORFINDER EP-C580 ^{FF}	1.8 – 2.3	none	1.0 – 1.3	trowel	
Primer	FLOORFINDER EP-P285 ^{FF}	0.3 – 0.4 + 15% Water	optional QS 0,3 – 0,8 0.3 – 0.5	0.15 - 0.25	roller	
Substrate	Cementitious substrates according to the appropriate standards and approvals must be capable of bearing loads and be free of cracks and voids. Pull-off strength \geq 1.5 N/mm ² , this system is water vapour permeable, max. residual moisture < 6 - 8% CM, for magnesite screed <10% CM, anhydrite max. 1% residual moisture, attention for underfloor-heating <0.3% CM, with higher residual moisture and on substrates with moisture from the backside special measures must be taken or a damp proof membrane should be installed. Substrate preparation e.g. grinding or shot blasting, sweeping and vacuum-cleaning is mandatory. Consumptions are calculated with FLOORFINDER quartz sands and fillers. Usage of other quartz sands and fillers can cause changes of consumption and technical data.					
Note	Detailed application ins	Detailed application instructions are available upon request or refer to the technical product data sheet.				

Technical Data

	Property	Standard	Result
	Conductivity With ESD-polymeric dispersion or with conductive ESD sealer	EN 1081 EN 61340-4-1 EN 61340-4-5	$\leq 10^{6} \Omega$ (Rg) $\leq 10^{9} \Omega$ (Rg) $\leq 3.5 \times 10^{7} \Omega$ (Rg) < 100 Volt (body voltage)
	Compressive strength	EN 196 / ASTM C109	Ca 55 N/mm²
	Flexural strength	EN 196 /ASTM C109	Ca 16 N/mm ²
	E-Modulus	DIN 53504	Ca 7000 N/mm²
	Shore-Hardness	DIN EN 868	D80 after 28 d
	Water-vapour permeability	DIN 5261523/50-95	μ= 4000
	Adhesive strength	EN ISO 4624	> 2,5 N/mm ² (concrete failure)
	Impact strength	EN 13813	≥ 4 Nm (IR4)
	Wear resistance (Taber)	EN ISO 5470-1	≤ 80 mg
	Low emission	AgBB and M1 and z.B.	Fulfilled after 3 days
	Fire resistance	EN 13501-1	Bfl-S1

Remark: for further information please refer to the product data sheets or contact our technical service. All data are approximate values. Therefore, no liability claims can be derived from the system data sheet. As all FLOORFINDER data sheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue (see www.floorfinder.com.my or contact us directly)– all technical information is subject to change without prior notice. FLOORFINDER products are guaranteed against defective material and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies which can be obtained on request.

Manufacturer:

FLOORFINDER ASIA SDN. BHD. - A division of VIACOR VISION AG, SWITZERLAND | No. 28, Lorong Sungai Puloh 1A/KU6 | Jalan Sungai Puloh | Batu 5 3/4 Kapar | 42100 Klang | Selangor Darul Ehsan | Malaysia | Tel: +603 3290 7644 | <u>info@floorfinder.com.my</u> | <u>www.floorfinder.com.my</u> Seite 2/2 Version Nr. 1 Stand: 08-2024