

## **FLOORFINDER**

## PERM protective FF

Water-vapour permeable epoxy resin based coating system, low odour, low emission, water-proof surface with good mechanical and chemical properties for minor loads and a wide colour spectrum.

#### Application Fields

Storage rooms

**Technical rooms** 

Areas with moisture sensitive substrates

Garages

**Production areas** 

Cellars

Walls

**Public buildings** 

# FLOORFINDER EP-P285FF SCRATCH COAT

FLOORFINDER EP-P285<sup>FF</sup>

PRIMER



#### SYSTEM BUILD UP



FLOORFINDER
EP-S680FF

2nd
SEALER

FLOORFINDER
EP-S680FF

1st

1st SEALER

### **SYSTEM HIGHLIGHTS**

0.2 - 0.6 mm System thickness





Impermeable to liquids



Low emission acc. AgBB and other standards



Bfl-s1 after EN 13501



Good chemical resistance



High abrasion resistance



High impact resistance



Low odor










## FLOORFINDER **PERM** protective FF

#### **Application and Consumption**

Layer	Product	Consumption (kg/m²)	Thickness (mm)	Application
2nd Sealer gloss or semi-glossy	FLOORFINDER EP-S680 <sup>FF</sup> or FLOORFINDER EP-S6801 <sup>FF</sup>	0.25 – 0.4 + 3 - 5 % Water 0.25 – 0.4 + 3 % Water	0.15 - 0.2	roller, squeegee + roller
1st Sealer gloss or semi-glossy	FLOORFINDER EP-S680 <sup>FF</sup> or FLOORFINDER EP-S6801 <sup>FF</sup>	0.25 – 0.4 + 3 - 5 % Water 0.25 – 0.4 + 3 % Water	0.15 - 0.2	roller, squeegee + roller
(optional) Scratch coat, levelling layer	FLOORFINDER EP-P285 <sup>FF</sup>	0,5 – 1.0 + 5 – 10 % Water + 50 - 100% QS 0.1 – 0.4	0.5 – 1.5	trowel
Primer	FLOORFINDER EP-P285FF	0.2 – 0.4 + 15 % Water	ca 0.1	roller, squeegee + roller
(optional) Primer	FLOORFINDER EP-S680 <sup>FF</sup> or FLOORFINDER EP-S6801 <sup>FF</sup>	0.2 – 0.4 + 7 - 10% Water	ca 0.1	roller, squeegee + roller
Substrate	Cementitious substrates according to the appropriate standards and approvals must be capable of bearing loads and be free of cracks and voids. Pull-off strength $\geq 1.5 \text{ N/mm}^2$ , this system is water vapour permeable, max. residual moisture < 6 - 8% CM, for magnesite screed <10% CM, anhydrite max. 1% residual moisture, attention for underfloor-heating <0.3% CM, with higher residual moisture and on substrates with moisture from the backside special measures must be taken or a damp proof membrane should be installed. Substrate preparation e.g. grinding or shot blasting, sweeping and vacuum-cleaning is mandatory. Consumptions are calculated with FLOORFINDER quartz sands and fillers. Usage of other quartz sands and fillers can cause changes of consumption and technical data.			
Note	Detailed application instructions are available upon request or refer to the technical product data sheet.			

#### **Technical Data**



Property	Standard	Result
Compressive strength	EN 196 / ASTM C109	ca 55 N/mm²
Flexural strength	EN 196 /ASTM C109	ca 16 N/mm²
E-Modulus	DIN 53504	ca 7000 N/mm²
Shore-Hardness	DIN EN 868	D80 after 28 d
Water-vapour permeability	DIN 5261523/50-95	μ= 4000
Adhesive strength	EN ISO 4624	> 2,5 N/mm² (concrete failure)
Impact strength	EN 13813	≥ 4 Nm (IR4)
Wear resistance (Taber)	EN ISO 5470-1	≤ 80 mg
Low emission	AgBB and M1 and z.B.	Fulfilled after 3 days
Fire resistance	EN 13501-1	Bfl-S1

Remark: for further information please refer to the product data sheets or contact our technical service. All data are approximate values. Therefore, no liability claims can be derived from the system data sheet. As all FLOORFINDER data sheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue (see www.floorfinder.com.my or contact us directly)- all technical information is subject to change without prior notice. FLOORFINDER products are guaranteed against defective material and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies which can be obtained on request.