floorfinder.

SYSTEM DATA SHEET

FLOORFINDER *UNIVERSAL SR ^{FF}*

Slip resistant, versatile epoxy resin based coating system, hard-wearing, with good mechanical and chemical properties and a wide spectrum of colours and surface structures.






SYSTEM HIGHLIGHTS

2.0 – 5.0 mm System thickness





floorfinder.

FLOORFINDER UNIVERSAL FF

Application and Consumption

Layer2	Product	Consumptio n (kg/m²)	Sand broadcasting (kg/m²)	Thickness (mm)	Application
Optional: Matt sealer, transparent	FLOORFINDER PU-S6005 FF	0.12 - 0.14	none	0.11 - 0.13	Microfibre roller
Sealer, pigmented	FLOORFINDER EP-S600 FF FLOORFINDER EP-S602 FF		none	0.3 - 0.8	squeegee and roller
Alternative: Sealer, transparent (for coloured quartz sand)	FLOORFINDER EP-T712 FF	0.5 – 1.0			
Wear coat, broadcasted with natural or coloured quartz sand	FLOORFINDER EP-C500 FF	1.5 - 3.0	QS (0.3-0.8 mm or 0.6-1.2 mm) or QCV in excess	2.5 - 5.5	notched trowel or squeegee
Optional: Scratch coat, levelling layer	FLOORFINDER EP-C500 FF (fillable 10-20% of FLOORFINDER QNV0)	0.8 - 2.0 (+ 0.08 - 0.4 QNV0)	None	0.5 – 2.0	trowel or rubber squeegee / notched trowel or squeegee
Primer	FLOORFINDER EP-T703 ^{FF} or FLOORFINDER EP-P210 ^{FF}	0.3 – 0.5	Optional QS (0.3-0.8 mm) Ca. 0.5	0.2 – 0.3	Rubber squeegee, roller
Substrate	Cementitious substrates according to the appropriate standards and approvals must be capable of bearing loads and be free of cracks and voids. Pull-off strength \geq 1.5 N/mm ² , residual moisture content < 4 %-CM, with higher residual moisture and on substrates with moisture from the backside special measures must be taken or a damp proof membrane must be installed. Substrate preparation e.g. grinding or shot blasting, sweeping and vacuum-cleaning is mandatory. Consumptions are calculated with FLOORFINDER quartz sands and fillers. Usage of other quartz sands and fillers can cause changes of consumption and technical data.				
Note	Detailed application instructions are available upon request or refer to the technical product data sheet. Do not use matt sealer in chemical loaded areas or permanent wet areas. In kitchens we recommend a with colored quartz sand broadcasted surface sealed with FLOORFINDER PU-S667N to avoid discolorations caused by food and beverage.				

Technical Data



	Property	Standard	Result
	Compressive strength	EN 196 / ASTM C109	Ca. 70 N/mm²
	Flexural strength	EN 196 / ASTM C109	Ca. 40 N/mm²
100	E-Modulus	DIN 53504	Ca. 7000 N/mm²
	Shore-Hardness	EN ISO 868	D 82 after 28 d
	Adhesive strength	EN ISO 4624	> 2,5 N/mm² (concrete failure)
	Impact strength	EN 13813	≥ 4 Nm (IR4)
	Wear resistance (Taber)	EN ISO 5470-1	≤ 55 mg
	Chemical resistance	EN ISO 2812-1	Test liquids 3, 10, 11 (more upon request)
	Slip resistance	DIN 51131 / BGR 181	R10 – R12
	Fire resistance	DIN EN 13501-1	B _{fl} -s1

Remark: for further information please refer to the product data sheets or contact our technical service. All data are approximate values. Therefore, no liability claims can be derived from the system data sheet. As all FLOORFINDER data sheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue (see www.floorfinder.com.my or contact us directly)- all technical information is subject to change without prior notice. FLOORFINDER products are guaranteed against defective material and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies which can be obtained on request.

Manufacturer:

 FLOORFINDER ASIA SDN. BHD. - A division of VIACOR VISION AG, SWITZERLAND | No. 28, Lorong Sungai Puloh 1A/KU6 | Jalan Sungai Puloh | Batu 5 3/4 Kapar | 42100 Klang |

 Selangor Darul Ehsan | Malaysia | Tel: +603 3290 7644 | info@floorfinder.com.my | www.floorfinder.com.my

 Seite 2/2

 Version Nr. 1