

FLOORFINDER UNIVERSAL voltex FF

Conductive, versatile epoxy resin based coating system, low emission, with hardwearing and good mechanical and chemical properties and a wide spectrum of colours and surface structures. Accord. to DIN EN 1081 and DIN EN 61340-4-1.

Application Fields

Logistic sites

Chemical Industry

Electronic Industry

Generator rooms

Surgery rooms

Laboratories

Technical rooms

Technical rooms

DISSIPATIVE

EMULSSION

SEALER (OPTIONAL)

FLOORFINDER

EP-C540 ASFF

FLOOR

FLOORFINDER EP-E480^{FF}



FLOORFINDER EP-C500FF

SCRATCH COAT




FLOORFINDER EP-T703FF



SYSTEM BUILD UP



SYSTEM HIGHLIGHTS



Conductive acc. DIN EN 1081, DIN EN 61340-4-1



Hygienic



High impact resistance



Capable of bearing load



Optionally slip resistance



Good chemical resistance









FLOORFINDER UNIVERSAL voltex FF

Application and Consumption

Layer	Product	Consumptio n (kg/m²)	Sand broadcasting (kg/m²)	Thickness (mm)	Application
Optional: Dissipative Floor Emulsion	TASKI Jontec ESD				
Self-levelling coating, conductive	FLOORFINDER EP-C540 AS FF	1.5 – 1.8	Optional: SIC F70 (0.18-0.25 mm) 0,02 – 0,08	1.0 – 1.2	notched trowel or squeegee + spike roller
Conductive layer, incl. copper tape	FLOORFINDER EP-E480 FF	0.08 - 0.10 +20% Water	none	0.06 - 0.08	rubber squeegee, roller
Optional: Scratch coat, levelling layer	FLOORFINDER EP-C500 FF (fillable 10-20% with FLOORFINDER QNV0)	0.8 - 2.0 (+ 0.08 - 0.4 QNV0)	none	0.5 – 2.0	trowel or rubber squeegee / notched trowel or squeegee
Primer	FLOORFINDER EP-T703 FF or FLOORFINDER EP-P210 FF	0.3 – 0.5	Optional: QS (0.3-0.8 mm) Ca. 0.5	0.2 - 0.3	Rubber squeegee, roller
Substrate	Cementitious substrates according to the appropriate standards and approvals must be capable of bearing loads and be free of cracks and voids. Pull-off strength ≥ 1.5 N/mm², residual moisture content < 4 %-CM, with higher residual moisture and on substrates with moisture from the backside special measures must be taken or a damp proof membrane must be installed. Substrate preparation e.g. grinding or shot blasting, sweeping and vacuum-cleaning is mandatory. Consumptions are calculated with FLOORFINDER quartz sands and fillers. Usage of other quartz sands and fillers can cause changes of consumption and technical data.				
Note	Detailed application instructions are available upon request or refer to the technical product data sheet				
Polymeric dispersion	To improve cleanability, a conductive polymeric dispersion can be applied on top of the cured sealer (e.g., TASKI Jontec ESD, $2x$ ca. $40-50$ ml/m²)				

Technical Data







Property	Standard	Result
Compressive strength	EN 196 / ASTM C109	Ca. 70 N/mm²
Flexural strength	EN 196 / ASTM C109	Ca. 40 N/mm²
Conductivity	EN 1081 EN 61340-4-1	$\leq 10^6 \Omega (Rg)$ $\leq 10^9 \Omega (Rg)$
Shore-Hardness	EN ISO 868	D 82 after 28 d
Adhesive strength	EN ISO 4624	> 2,5 N/mm² (concrete failure)
Impact strength	EN 13813	≥ 4 Nm (IR4)
Wear resistance (Taber)	EN ISO 5470-1	≤ 55 mg
Chemical resistance	EN ISO 2812-1	Test liquids 3, 10, 11 (more see chemical resistance list
Solvent free	Test method "Deutsche Bauchemie"	≤ 1 %
Fire resistance	DIN EN 13501-1	B _{fl} -s1

Remark: for further information please refer to the product data sheets or contact our technical service. All data are approximate values. Therefore, no liability claims can be derived from the system data sheet. As all FLOORFINDER data sheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue (see www.floorfinder.com.my or contact us directly)- all technical information is subject to change without prior notice. FLOORFINDER products are guaranteed against defective material and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies which can be obtained on request.