

**Product 02456510** 4-comp. PU coating, solvent-free, semi-gloss, coloured, UV coating

## 1 General Data

### Fields of application

FLOORCRETE PU-TC UV<sup>FF</sup> is used as a protective coating in situations subject to constant exposure to aggressive chemicals, and mechanical abuses such as dairy, food & beverage production facilities, warehouse & distribution centres, chemical and minerals processing plants and waste treatment plants. It is normally used as a top coat over FLOORCRETE PU-MF<sup>FF</sup> wear coat broadcast.

### Product description

FLOORCRETE PU-TC UV<sup>FF</sup> is a 4-component, high build polyurethane coating. It has excellent mechanical and chemical properties. It is resistant to organic acids, dilute mineral acids, vegetable and animal fats, petroleum oils and solvents. FLOORCRETE PU-TC UV<sup>FF</sup> has improved resistance when exposed to UV and weathering compared to conventional FLOORCRETE PU-TC<sup>FF</sup>. It is suitable for use in conditions of a wide temperature range between 0°C and +100°C.

### Characteristics

- Excellent chemical resistance
- High impact/abrasion resistance
- Fast curing
- Semi-gloss finish
- Odorless
- Solvent free
- Improved UV resistance compare to conventional FLOORCRETE PU-TC<sup>FF</sup>
- Wide service temperatures

### FLOORCRETE systems

FLOORCRETE PU-TC UV<sup>FF</sup> is the top coat for the FLOORCRETE system:  
FLOORCRETE **MF STANDARD SR<sup>FF</sup>**



#### (A) Technical data

##### Liquid mixture (A+B +C)

1. Solids content	99 %
2. Density (25°C)	1.34 g/cm <sup>3</sup>
3. Viscosity (25°C)	A+B: 1000 -1500 mPas
4. Packaging size (4-component)	3.3 kg (+ 0.175 kg colour paste) (1 kg A + 1.3 kg B + 1 kg C + 0.175 kg colour paste)
5. Colour	Green, buff, red, grey, beige, light grey
6. Shelf life	9 months in closed original container
7. Storage	Dry at 10–30°C, avoid direct sunlight

#### (B) Technical data

##### Cured material

1. Adhesive strength (DIN ISO 4624)	> 1.5 N/mm <sup>2</sup> (concrete failure)
2. Hardness (DIN EN ISO 868)	Shore D56 after 7 days Shore D65 after 28 days

### Care and maintenance

The lifespan & performance of your resin floor can be extended considerably by adopting a regular cleaning and care programme. We recommend the use of an alkaline based cleaning agent.

### Technical support

For system build up possibilities and detailed information relating to the laying of FLOORCRETE products, please refer to the FLOORCRETE System Planner or contact Floorfinder Asia Sdn Bhd directly.

Tel: +603 3290 7644

e-mail: [info@floorfinder.com.my](mailto:info@floorfinder.com.my)

#### Manufacturer:

Floorfinder Asia Sdn. Bhd., No. 28, Lorong Sungai Puloh 1A/KU6, Jalan Sungai Puloh, Batu 5 3/4, Kapar, 42100 Klang, Selangor Darul Ehsan, Malaysia, tel: +603 3290 7644, email: [info@floorfinder.com.my](mailto:info@floorfinder.com.my) , [www.floorfinder.com.my](http://www.floorfinder.com.my) – A division of VIACOR VISION AG, SWITZERLAND

**Product 02456510** 4-comp. PU coating, solvent-free, semi-gloss, coloured, UV coating

## 2 Application method

### Substrate preparation

FLOORCRETE PU-TC UV<sup>FF</sup> is applied directly onto the cleaned FLOORCRETE PU-MF<sup>FF</sup> wear coat, which is broadcast with quartz sand or other aggregates (within 24 and hours) as FLOORCRETE topping system without grinding the surface. If longer than 24 hours, a light grind is required. Furthermore, it could be applied on FLOORCRETE PU-VC<sup>FF</sup> skirting's and vertical applications.

### Primer

No primer is required on existing FLOORCRETE PU-MF<sup>FF</sup> broadcast wear coat.

### Application

Before starting the application, the material temperature must be close to the site conditions.

Dispense the colour paste into component A. Mix to disperse the colour paste (1 minute) until homogeneous, add Component B and mix using a helical mixer at a speed of 350 rpm until homogeneously.

Add component C gradually to the mix with the mixer running. Move the mixer around from side to side and top to bottom and scrap the sides of the mixing vessel to ensure thorough mixing, until homogeneous (2 – 3 minutes).

Transfer the mixture to another clean container and mix for 1 minute.

The mixed material is poured onto the surface and spread over the entire area using a hard or soft rubber squeegee. Then it is rolled with a short-piled microfiber roller (e. g. Multitool microfiber 6 or 8 mm) in one direction. The formation of puddles should be avoided. As finish we recommend to roll in one direction with the microfiber roller. Ensure to maintain continuity of wet material between pours.

Subsets cannot be mixed because only complete sacks of filler may be processed.

For cleaning of tools and other contaminations use FLOORFINDER SO-X10 tool cleaner.

### (C) Technical data

#### Liquid mixture (A+B)

1. Mixing ratio A : B : C : CP	1 : 1.3 : 1 : 0.175 by weight (kg)
2. Working time (25°C)	approx. 20-25 minutes
3. Application temperature	10 – 30°C (min. 3°C above dew point)
4. Material consumption	0.4 – 0.8 kg/m <sup>2</sup>
5. Overcoating (25°C)	within 16 – 24 hours
6. Cure time to withstand:	
Foot traffic	after 24 hours
Heavy traffic	after 3 days
Exposure to chemical	after 7 days

Note : For low temperature application, addition of accelerator is required. For detailed information, please contact Floorfinder Asia Sdn Bhd directly.

### Overcoating

Overcoating should be carried out within 24 hours after application of FLOORCRETE PU-TC UV<sup>FF</sup>. If longer than 24 hours, it is necessary to lightly grind the surface before over-coating is carried out.

#### Manufacturer:

Floorfinder Asia Sdn. Bhd., No. 28, Lorong Sungai Puloh 1A/KU6, Jalan Sungai Puloh, Batu 5 3/4, Kapar, 42100 Klang, Selangor Darul Ehsan, Malaysia, tel: +603 3290 7644, email: [info@floorfinder.com.my](mailto:info@floorfinder.com.my) , [www.floorfinder.com.my](http://www.floorfinder.com.my) – A division of VIACOR VISION AG, SWITZERLAND

Product 02456510 4-comp. PU coating, solvent-free, semi-gloss, coloured, UV coating

### 3 Further information

#### CE-Mark



#### CE-Mark according to EN 13813

EN 13813: 2003-01, Screed material and floor screeds - Screed materials - Properties and requirements is the basis for requirements for floor screeds used in indoor flooring constructions. Resin coatings and sealer are also subject to this norm.

Details see CE-conformity mark and conformity declaration.

#### Warnings and precautions

Information relating to the safe handling of this product can be found in the Material Safety Data Sheet. Local regulations concerning the safe handling of epoxy resin-based coating materials must be observed.

Suitable protective clothing including suitable eye protection must be worn.

#### Disclaimer

All information in this technical data sheet is based on our current knowledge and experience. This does not release the applicator from performing their own tests as many application factors, beyond our control, affect the application of our product. No guarantee of characteristics or suitability for a special purpose can be derived from this information. All present data, descriptions, drawings, photos, ratios, weights etc. are subject to change without prior notice and do not represent contracted characteristics of the product.

Due to different materials, sub-bases and working conditions, no guarantee of an application result or any liability claims can be derived from these details or from an unwritten technical advice except for liability claims based on:

-damage to life, body or health resulting from a negligent violation of obligations or a deliberate or negligent violation of obligation of a legal representative or assistant and

-if we are charged with intention or gross negligence.

The user has to test the products for their intended use. The user is responsible for following existing laws and orders and for observing third party trade mark rights.

As all Floorfinder data sheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue (see [www.floorfinder.com.my](http://www.floorfinder.com.my)).

#### Manufacturer:

Floorfinder Asia Sdn. Bhd., No. 28, Lorong Sungai Puloh 1A/KU6, Jalan Sungai Puloh, Batu 5 3/4, Kapar, 42100 Klang, Selangor Darul Ehsan, Malaysia, tel: +603 3290 7644, email: [info@floorfinder.com.my](mailto:info@floorfinder.com.my) , [www.floorfinder.com.my](http://www.floorfinder.com.my) – A division of VIACOR VISION AG, SWITZERLAND