

#### FLOORFINDER EP-S600 FF

#### **Technical Data Sheet**

Product 01460000 2-comp. EP sealer, solvent-free, colored

## 1 General Data

## Fields of application

FLOORFINDER EP-S600 FF is suitable for use for protection of concrete surface against abrasion and chemicals in areas subject to foot and light vehicular traffic such as walkways, workshops, production facilities, warehouses, car park decks, garages and plant rooms.

### **Product description**

FLOORFINDER EP-S600 FF is a colored, solvent free, two-component high quality epoxy resin. It is resistant to petroleum oils, solvents, acids & alkalis and shows good wear and slip resistance.

In general, epoxy coatings are not colour stable if exposed to UV light or under influence of weathering. We recommend to over-coat with a colour stable sealer.

#### Features & Benefits

- Durable 99% solids provide a 500 microns dried film thickness (two coat application)
- · High gloss finish
- Solvent free non-flammable
- Good Chemical resistant
- Wear resistant
- Slip resistant can provide R11 to R13 rating with quartz aggregates
- Low / no odour
- · Aesthetic flexibility in color

## **FLOORFINDER systems**

FLOORFINDER EP-S600  $^{\rm FF}$  is used as a top coat for the following FLOORFINDER systems:

FLOORFINDER **PROTECTIVE** FF FLOORFINDER **DECK OS8** FF

#### Care and maintenance

The lifespan and performance of your resin floor can be extended considerably by adopting a regular cleaning and care programme. We recommend the use of an alkaline based cleaning agent.

(A) Technical data				
Liquid mixture (A+B)				
1.	Solids content	99 %		
2.	Density (25°C)	1.46 g/cm <sup>3</sup>		
3.	Viscosity (28°C)	2000-3000 mPas		
4.	Packaging size	20 kg (16 kg A + 4 kg B) 5 kg ( 4 kg A + 1 kg B)		
5.	Colors	FLOORFINDER standard		
6.	Shelf life	12 months in closed original container		
7.	storage	Dry at 10–30°C, avoid direct sunlight		

(B) Technical data				
Cured material				
1.	Adhesive strength (DIN ISO 4624)	> 1.5 N/mm² (concrete failure)		
2.	Shore D hardness (DIN EN ISO 88)	78 (Day 1) 83 (Day 7)		
3.	Abrasion resistance (DIN EN ISO 5470-1)	70 mg/1000 cycles (Taber CS10 wheel)		

#### Technical support

For system build up possibilities and detailed information relating to the laying of FLOORFINDER products, please refer to the FLOORFINDER System Planner or contact Floorfinder Asia Sdn. Bhd. directly.

Tel: +603 3290 7644 e-mail: info@floorfinder.com.my

#### Manufacturer

Floorfinder Asia Sdn. Bhd., No. 28, Lorong Sungai Puloh 1A/KU6, Jalan Sungai Puloh, Batu 5 3/4, Kapar, 42100 Klang, Selangor Darul Ehsan, Malaysia, tel: +603 3290 7644, email: info@floorfinder.com.my , www.floorfinder.com.my – A division of VIACOR VISION AG, SWITZERLAND



#### FLOORFINDER EP-S600 FF

#### **Technical Data Sheet**

Product 01460000 2-comp. EP sealer, solvent-free, colored

# 2 Application method

#### Substrate preparation

The substrate must be firm, clean, dry and have a tensile strength of 1.5 N/mm² minimum.

Wet areas shall be dried with a blow torch. The moisture content in the substrate must not exceed 4 CM %.

New concrete must be allowed to cure for a minimum of 28 days.

Repair imperfections (holes and cracks) with an epoxy patching compound such as FLOORFINDER EP-T703 FF where necessary.

Remove surface laitance, contaminants, coating, curing compound and all weak and loose materials.

Prepare substrate by Captive Shot Blasting or Diamond Grinding to provide the appropriate surface profile for optimum mechanical keying.

If FLOORFINDER EP-S600  $^{\rm FF}$  is used as a top coat over an existing EP or PU underlay / topping, it can be applied directly on the existing surface if the underlay / topping is newly laid (within 16 – 24 hrs) otherwise a light grinding is necessary.

# Application

Before starting the application, the material temperature must be close to site conditions.

Mix Component A for 2-3 minutes.

Empty contents of component B (Hardener) into component A (Base Resin). Mix with a suitable mixer at a speed of 500 rpm to avoid incorporating excessive air into the mix. Mix for 2-3 minutes.

Transfer the mixture into another clean container and mix for 1-2 minute.

To cover vertical surfaces, add 1 to 3 % of FLOORFINDER X955 (thixotropic agent) and mix for 1 minute or until homogeneous.

Spread the mixed product onto the surface with a squeegee and back roll with a short nap roller.

For cleaning of tools and other contaminations use FLOORFINDER SO-X10 cleaner.

# Overcoating

The second coat can be applied within 24 hrs without grinding. If longer, the surface has to be grinded before over-coating.

(C) Technical data  Liquid mixture (A+B)				
2.	Working time (25°C)	approx. 20-25 minutes		
3.	Application temperature:	10 – 30°C (min. 3° above dew point)		
4.	Material consumption			
	on smooth surfaces	250 - 300 g/m <sup>2</sup>		
	on broadcasted surfaces	400 – 600 g/m <sup>2</sup>		
5.	Overcoating (25°C)	within 16- 24hours		
6.	Cure time to withstand:			
	Foot traffic (25 °C) Heavy Traffic (25°C) Exposure to chemicals (25°C)	after 16 - 24 hours after 3 days after 7days		

# Manufacturer:

Floorfinder Asia Sdn. Bhd., No. 28, Lorong Sungai Puloh 1A/KU6, Jalan Sungai Puloh, Batu 5 3/4, Kapar, 42100 Klang, Selangor Darul Ehsan, Malaysia, tel: +603 3290 7644, email: info@floorfinder.com.my , www.floorfinder.com.my – A division of VIACOR VISION AG, SWITZERLAND



#### FLOORFINDER EP-S600 FF

#### **Technical Data Sheet**

Product 01460000 2-comp. EP sealer, solvent-free, colored

## 3 Further information

**CE-Mark** 



#### **CE-Mark according to EN 13813**

EN 13813: 2003-01, Screed material and floor screeds - Screed materials - Properties and requirements is the basis for requirements for floor screeds used in indoor flooring constructions. Resin coatings and sealer are also subject to this norm.

Details see CE-conformity mark and conformity declara-

### Warnings and precautions

Information relating to the safe handling of this product can be found in the Material Safety Data Sheet. Local regulations concerning the safe handling of epoxy resin-based coating materials must be observed.

Suitable protective clothing including suitable eye protection must be worn.

# Disclaimer

All information in this technical data sheet is based on our current knowledge and experience. This does not release the applicator from performing their own tests as many application factors, beyond our control, affect the application of our product. No guarantee of characeristics or suitability for a special purpose can be derived from this information. All present data, descriptions, drawings, photos, ratios, weights etc. are subject to change without prior notice and do not represent contracted characteritics of the product.

Due to different materials, sub-bases and working conditions, no guaratee of an application result or any liability claims can be derived from these details or from an unwritten technical advice except for liability claims based on:

-damage to life, body or health resulting from a negligent violation of obligations or a deliberate or negligent vialation of obligation of a legal representative or assistant and

-if we are charged with intention or gross negligence.

The user has to test the products for their intended use. The user is responsible for following existing laws and orders and for observing third party trade mark rights.

As all Floorfinder data sheets are updated on a regular basis it is the users responsibility to obtain the most recent issue (see www.floorfinder.com.my).

#### Manufacturer:

Floorfinder Asia Sdn. Bhd., No. 28, Lorong Sungai Puloh 1A/KU6, Jalan Sungai Puloh, Batu 5 3/4, Kapar, 42100 Klang, Selangor Darul Ehsan, Malaysia, tel: +603 3290 7644, email: <a href="mailto:info@floorfinder.com.my">info@floorfinder.com.my</a>, <a href="https://www.floorfinder.com.my">www.floorfinder.com.my</a> – A division of VIACOR VISION AG, SWITZERLAND