

**FLOORFINDER PU-T711<sup>FF</sup> Technical Data Sheet**

**Product 02071100** 1-comp. PU binder for stone carpets, UV and colour stable, low emission

**1 General Data**

**Fields of application**

FLOORFINDER PU-T711<sup>FF</sup> is used as UV- and colour-stable, transparent binder for VIASOL colour quartz mortars. It has a glossy finish.  
FLOORFINDER PU-T711<sup>FF</sup> contains a reaction starter which may lead to odours during the first days of curing. Therefore, the product should only be used OUTDOORS. Typical uses are balcony and terraces, parking areas and other areas outdoors.

**Product description**

FLOORFINDER PU-T711<sup>FF</sup> is a UV and colour-stable, transparent, low emission, one-component PU sealer based on high quality aliphatic polyurethane resin. The product shows good chemical resistance against diluted acids and alkalis, salt and wastewater and lubricant and oils.

**Care and maintenance**

For a long-term preservation of the properties of resin floors, we recommend a regular cleaning and care programme. For further details see our FLOORFINDER Care and Maintenance Guide. Before first use we recommend to perform a basic cleaning and initial care.

**Technical support**

For system build up possibilities and detailed information relating to the laying of FLOORFINDER products, please refer to the FLOORFINDER System Planner or contact Floorfinder Asia Sdn. Bhd. directly.  
Tel: +603 3290 7644  
e-mail: [info@floorfinder.com.my](mailto:info@floorfinder.com.my)

| <b>(A) Technical Data</b>                 |   |
|---|---|
| <b>Mixture (A+B)</b>                      |   |
| 1. Solids content                         | >99%  |
| 2. Density (25°C)                         | ca. 1.153 g/cm <sup>3</sup>                               |
| 3. Viscosity (25°C)                       | 1780 - 2000 mPas  |
| 4. Packaging size (1-component container) | 10 kg   |
| 5. Colour                                 | transparent, glossy                                       |
| 6. Shelf life (20°C)                      | 3 months  |
| 7. Storage                                | Dry at 15-25°C, avoid direct sunlight, protect from frost |

| <b>(B) Technical Data</b>              |                         |
|--|-------------------------|
| <b>Cured material</b>                  |                         |
| 1. Adhesive strength (DIN EN ISO 4624) | > 1,5 N/mm <sup>2</sup> |

**Manufacturer:**

Floorfinder Asia Sdn. Bhd., No. 28, Lorong Sungai Puloh 1A/KU6, Jalan Sungai Puloh, Batu 5 3/4, Kapar, 42100 Klang, Selangor Darul Ehsan, Malaysia, tel: +603 3290 7644, email: [info@floorfinder.com.my](mailto:info@floorfinder.com.my) , [www.floorfinder.com.my](http://www.floorfinder.com.my) – A division of VIACOR VISION AG, SWITZERLAND

**FLOORFINDER PU-T711<sup>FF</sup> Technical Data Sheet**

**Product 02071100** 1-comp. PU binder for stone carpets, UV and colour stable, low emission

**2 Application method**

Please also refer to our general application guideline.

**Substrate Preparation**

The substrate must be clean and free of dust and loose particles. All traces of contaminants such as oils, fats, greases, paint residues, chemicals, algae and laitance should be removed.

FLOORFINDER PU-T711<sup>FF</sup> is applied directly on primed surfaces sprinkled with quartz sand e. g. with FLOORFINDER EP-P210<sup>FF</sup> or on FLOORSEAL coatings like FLOORFINDER PU-M1003<sup>FF</sup>.

**Application**

FLOORFINDER PU-T711<sup>FF</sup> is supplied in 1-component containers. The product temperature should be between 15°C (pre-heat if necessary) and 30°C as a maximum.

Fillers (coloured quartz sand etc.) must be fire dried. Only one-grain size quartz sand is used. First add the filler to the mixer and then FLOORFINDER PU-T711<sup>FF</sup> in the right mixing ratio. Mix until the mixture is homogeneous.

The mixture is spread with a trowel onto the prepared substrate and smoothed manually.

The mixing ratio for binder to filler depends on the grain size of the filler and ambient conditions. We recommend using 5-8% of binder depending on grain size and grain size distribution.

Example:

| thickness | Consumption mortar | Amount of binder              |
|-----------|--------------------|-------------------------------|
| ≥ 5 mm    | ca. 10 kg          | ca. 0.8-0.9 kg/m <sup>2</sup> |
| ≥ 8 mm    | ca. 16 kg          | ca. 0.9-1.0 kg/m <sup>2</sup> |
| ≥ 12 mm   | ca. 24 kg          | ca. 1.1-1.3 kg/m <sup>2</sup> |

The mixture should not be too wet, otherwise a concentration of the binder at the bottom may occur and lead to foaming and reduced adhesion to the substrate.

High temperatures and high air humidity will shorten pot life and curing time, low temperatures and low air humidity will increase pot life and curing time.

For cleaning of tools and other dirt FLOORFINDER SO-X12 cleaner is recommended.

**Please note:** As the product cures in contact with air humidity, please only use full containers of FLOORFINDER PU-T711<sup>FF</sup>.

| <b>(C) Technical Data</b>   |   |
|---|---|
| <b>Mixture (A+B)</b>  |   |
| 1. Mixing ratio   | 1 component   |
| 2. Consumption sealer (ca. 0,3 mm) stone carpet (1 mm thickness)          | 250 - 350 g/ m <sup>2</sup><br>ca. 600 g/ m <sup>2</sup> binder +<br>300 g quartz sand 0,4-0,7 mm |
| 3. Working time (20 °C)<br>(30 °C)  | approx. 60 min.<br>Approx. 25 min   |
| 4. Application temperature  | 15 – 25 °C (material)<br>10 – 30°C (object)<br>(min. 3 K above dew point)                         |
| 5. Relative humidity  | 30 to max. 80%  |
| 6. Foot traffic (20°C)  | after 12 - 18 hours   |
| 7. Fully capable of withstanding stress mechanical (20°C) chemical (20°C) | after 3 days<br>after 7 days  |

**Overcoating**

It is not necessary to abrade the surface if the following coat is applied within 24 h. After 24 h, the application can only take place after a careful grinding of the surface.

**Manufacturer:**

Floorfinder Asia Sdn. Bhd., No. 28, Lorong Sungai Puloh 1A/KU6, Jalan Sungai Puloh, Batu 5 3/4, Kapar, 42100 Klang, Selangor Darul Ehsan, Malaysia, tel: +603 3290 7644, email: [info@floorfinder.com.my](mailto:info@floorfinder.com.my) , [www.floorfinder.com.my](http://www.floorfinder.com.my) – A division of VIACOR VISION AG, SWITZERLAND

**FLOORFINDER PU-T711<sup>FF</sup> Technical Data Sheet**

Product 02071100 1-comp. PU binder for stone carpets, UV and colour stable, low emission

### 3 Further information

#### CE-Mark



#### CE-Mark according to EN 13813

EN 13813: 2003-01, Screed material and floor screeds - Screed materials - Properties and requirements is the basis for requirements for floor screeds used in indoor flooring constructions. Resin coatings and sealer are also subject to this norm.

Details see CE-conformity mark and conformity declaration.

#### Decopaint-Guidelines (EU 2004/42/EG)

The maximum allowable VOC content for Product Category IIA j Type Lb products (in the ready to use state) is:

Stage II (from 2010) < 500 g/l VOC

In the ready to use state, this product contains less than 500 g/l VOC.

#### Warnings and precautions

Information relating to the safe handling of this product can be found in the Material Safety Data Sheet. Local regulations concerning the safe handling of epoxy resin-based coating materials must be observed.

Suitable protective clothing including suitable eye protection must be worn.

#### Disclaimer

All information in this technical data sheet is based on our current knowledge and experience. This does not release the applicator from performing their own tests as many application factors, beyond our control, affect the application of our product. No guarantee of characteristics or suitability for a special purpose can be derived from this information. All present data, descriptions, drawings, photos, ratios, weights etc. are subject to change without prior notice and do not represent contracted characteristics of the product.

Due to different materials, sub-bases and working conditions, no guarantee of an application result or any liability claims can be derived from these details or from an unwritten technical advice except for liability claims based on:

-damage to life, body or health resulting from a negligent violation of obligations or a deliberate or negligent violation of obligation of a legal representative or assistant and  
-if we are charged with intention or gross negligence.

The user has to test the products for their intended use. The user is responsible for following existing laws and orders and for observing third party trade mark rights.

As all floorfinder asia data sheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue (see [www.floorfinder.com.my](http://www.floorfinder.com.my) or contact us directly).

#### Manufacturer:

Floorfinder Asia Sdn. Bhd., No. 28, Lorong Sungai Puloh 1A/KU6, Jalan Sungai Puloh, Batu 5 3/4, Kapar, 42100 Klang, Selangor Darul Ehsan, Malaysia, tel: +603 3290 7644, email: [info@floorfinder.com.my](mailto:info@floorfinder.com.my) , [www.floorfinder.com.my](http://www.floorfinder.com.my) – A division of VIACOR VISION AG, SWITZERLAND