

Product 07112000  
Product 07112100

Colored quartz sand for FLOORFINDER **DESIGN QCV<sup>FF</sup>**-systems

## 1 General data

### Field of application

FLOORFINDER QCV<sup>FF</sup> is used as quartz sand for sprinkle into the fresh coating system for e.g. in the systems FLOORFINDER **DESIGN QCV<sup>FF</sup>**.

### Product description

FLOORFINDER QCV<sup>FF</sup> are with epoxy resins coated natural and oven dried quartz sands in defined grain curve. FLOORFINDER QCV<sup>FF</sup> can in outdoor and sometimes in indoor applications yellowing by the influence of UV light. This depends on color and on intensity of UV. If special requirements for UV resistance is available use colored quartz sand which is coated with aliphatic PU colors.

### Application

FLOORFINDER QCV<sup>FF</sup> is sprinkled in the fresh wear coats FLOORFINDER EP-Q3600<sup>FF</sup> in excess. The consumption you can find in the FLOORFINDER DESIGN<sup>FF</sup> application guideline or in the system calculations. After curing, the wear coats with FLOORFINDER QCV<sup>FF</sup> colored quartz sands can be slightly grinded with a disk grinding machine (appr. 35 kg) and vacuum cleaned.

### Technical support

For system build up possibilities and detailed information relating to the laying of FLOORFINDER products, please refer to the FLOORFINDER System Planner or contact Floorfinder Asia Sdn Bhd directly.

Tel: +603 3290 7644  
e-mail: [info@floorfinder.com.my](mailto:info@floorfinder.com.my)

### Warnings and precautions

Information relating to the safe handling of this product can be found in the Material Safety Data Sheet. Local regulations concerning the safe handling of epoxy resin-based coating materials must be observed. Suitable protective clothing including suitable eye protection must be worn.

#### (A) Technical Data

##### Solid product

1. Solid content	100 %
2. Density	2.7 g/cm <sup>3</sup>
3. Bulk density	in middle 1.65 g/cm <sup>3</sup>
4. Container size	25 kg sacks or buckets
5. Shelf life (20 °C)	24 months
6. Storage conditions	dry at 5 – 25°C

### Disclaimer

All information in this technical data sheet is based on our current knowledge and experience. This does not release the applicator from performing their own tests as many application factors, beyond our control, affect the application of our product. No guarantee of characteristics or suitability for a special purpose can be derived from this information. All present data, descriptions, drawings, photos, ratios, weights etc. are subject to change without prior notice and do not represent contracted characteristics of the product.

Due to different materials, sub-bases and working conditions, no guarantee of an application result or any liability claims can be derived from these details or from an unwritten technical advice except for liability claims based on:

- damage to life, body or health resulting from a negligent violation of obligations or a deliberate or negligent violation of obligation of a legal representative or assistant and
- if we are charged with intention or gross negligence.

The user must test the products for their intended use. The user is responsible for following existing laws and orders and for observing third party trade mark rights.

As all Floorfinder Asia data sheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue (see [www.floorfinder.com.my](http://www.floorfinder.com.my) or contact us directly).

#### Manufacturer:

Floorfinder Asia Sdn. Bhd., No. 28, Lorong Sungai Puloh 1A/KU6, Jalan Sungai Puloh, Batu 5 3/4, Kapar, 42100 Klang, Selangor Darul Ehsan, Malaysia, tel: +603 3290 7644, email: [info@floorfinder.com.my](mailto:info@floorfinder.com.my) , [www.floorfinder.com.my](http://www.floorfinder.com.my) – A division of VIACOR VISION AG, SWITZERLAND